



# Stainless Steel

Typical filler metals for dissimilar joining Stainless Steel

	347, 347H	321, 321H	317	316L	316, 316H	310S	310	309S	309	308	304
<b>304H, 305, 304</b>	308R	308R	308R 316R (317)	308R 316R	308R 316R	308R 309R 310R	308R 309R 310R	308R 309R	308R 309R	308R	308R
<b>304L</b>	308R 347R	308R 347R	308R 316R (317)	308R 316R	308R 316R	308R 309R 310R	308R 309R 310R	308R 309R	308R 309R	308R	
<b>308</b>	308R 347R	308R	308R 316R (317)	308R 316R	308R 316R	308R 309R 310R	308R 309R 310R	308R 309R	308R 309R		
<b>309</b>	309R 347R	309R 347R	309R 316R	309R 316R	309R 316R	309R 310R	309R 310R	309R			
<b>309S</b>	309R 347R	309R 347R	309R 316R	309R 316R	309R 316R	309R 310R	309R 310R				
<b>310</b>	308R 310R	308R 310R	(317) 309Mo 310R	316R 309Mo 310R	316R 309Mo 310R	310R					
<b>310S</b>	308R 310R	308R 310R	(317) 309Mo	316R 309Mo	316R 309Mo						
<b>316H, 316</b>	308R 316R 347R	308R 316R	(317) 316R	316R							
<b>316L</b>	316R 347R	316R	(317)								
<b>317</b>	308R (317) 347R	308R (317)									
<b>321H, 321</b>	308R 347R										

For other base materials we recommend you to contact us for more detailed information.