



Aciers inoxydables

Métaux d'apport types pour l'assemblage hétérogène des aciers inoxydables

	347, 347H	321, 321H	317	316L	316, 316H	310S	310	309S	309	308	304
304H, 305, 304	308R	308R	308R 316R	308R 316R	308R 316R	308R 309R 310R	308R 309R 310R	308R 309R	308R 309R	308R	308R
304L	308R 347R	308R 347R	308R 316R	308R 316R	308R 316R	308R 309R 310R	308R 309R 310R	308R 309R	308R 309R	308R	
308	308R 347R	308R	308R 316R	308R 316R	308R 316R	308R 309R 310R	308R 309R 310R	308R 309R	308R 309R		
309	309R 347R	309R 347R	309R 316R	309R 316R	309R 316R	309R 310R	309R 310R	309R			
309S	309R 347R	309R 347R	309R 316R	309R 316R	309R 316R	309R 310R	309R 310R				
310	308R 310R	308R 310R	309Mo 310R	316R 309Mo 310R	316R 309Mo 310R	310R					
310S	308R 310R	308R 310R	309Mo	316R 309Mo	316R 309Mo						
316H, 316	308R 316R 347R	308R 316R	316R	316R							
316L	316R 347R	316R									
317	308R 347R	308R									
321H, 321	308R 347R										

Pour d'autres matériaux de base, nous vous conseillons de nous contacter pour plus de détails.