

HILCO HILCHROME 310R

Stick electrodes - stainless steel - heat resistant

AWS A5.4: E310-16

EN ISO 3581-A: E 25 20 R 1 2

Werkstoffnr. 1.4842

Coating type:

Rutile-basic

Current:

Welding positions:



Hilchrome 310R is our rutile-basic coated electrode for joining and surfacing 25Cr20Ni austenitic heat resistant Cr-, CrSi, CrNi and CrNiSi as well as ferritic-pearlitic CrAl steel grades. Maximum operating temperature in a non-sulphurous environment is 1150°C. When exposed to sulphurous gases (max. 2 g S/Nm3) we recommend a maximum working temperature up to 1040°C. Typical applications include annealing plants, hardening plants, steam boiler construction, crude oil industry and ceramic industry. Hilchrome 310R is core wire alloyed, AC/DC.

Base materials to be welded:

- ASTM/AISI Gr. 310 and similar heat resistant steels
- WNr. 1.4841, 1.4828, 1.4845, 1.4713, 1.4724, 1.4742, 1.4762
- Heat resisting rolled, forged and cast steels

Applications:

- Power Industry
- Repair & Maintenance

Chemical composition, wt. % weld metal - typical:

| С | Mn | Si | Cr | Ni |
|------|-----|-----|------|------|
| 0,12 | 2,0 | 0,5 | 26,0 | 21,0 |

Mechanical properties, weld metal - typical:

| roomannoar proportion | o, word motal typican | typiou | | | |
|---------------------------|----------------------------|-------------------------|-------------------------|--------------------------|--|
| Condition | 0,2% Yield strength MPa | Tensile strength MPa | Elongation Lo=5d - % | Impact Values ISO-V J | |
| As welded | ≥ 380 | ≥ 570 | ≥ 35 | 20°C ≥ 80 | |

Packaging and welding data:

| ionaging and notaing data. | | | | |
|----------------------------|--------|--------------|---------|--|
| Dia. | Length | Weight (kgs) | Current | |
| mm. | mm. | 1000 pcs. | Α | |
| 3,2 | 350 | 35,4 | 65-105 | |
| 4 0 | 350 | 48.0 | 100-140 | |

D-10. HILCO HILCHROME 310R Rev. 10